

Strip

Stainless Steel



WS-308L

Classification: ISO 14343-A B 19 9 L
SFA-5.9 EQ308L

C	Si	Mn	Cr	Ni	Mo	N	Nb
0.03	0.65	1.0-2.5	19.0-20.0	11.0-14.0	2.0-3.0	-	-

WS-309L

Classification: ISO 14343-B B 309 L
SFA-5.9 EQ309L

C	Si	Mn	Cr	Ni	Mo	N	Nb
0.03	0.50	1.0-2.5	23.0-25.0	12.0-14.0	-	-	-

WS-22 11 L

Classification: ISO 14343-A B 22 11 L
SFA-5.9 EQ309L

C	Si	Mn	Cr	Ni	Mo	N	Nb
0.03	0.50	1.0-2.5	21.0-23.0	10.5-12.0	-	-	-

WS-316L

Classification: ISO 14343-A B 19 12 3 L
SFA/AWS A 5.9 EQ316L

C	Si	Mn	Cr	Ni	Mo	N	Nb
0.03	0.50	1.0-2.5	18.0-20.0	11.0-14.0	2.0-3.0	-	-

WS-23 12 2L

Classification: ISO 14343-A B 23 12 2 L
SFA/AWS A 5.9 EQ309LMo

C	Si	Mn	Cr	Ni	Mo	N	Nb
0.03	0.50	1.0-2.5	21.0-22.5	11.0-14.0	2.0-3.5	-	-

WS-347L

Classification: ISO 14343-A B 19 9 LNb
SFA/AWS A 5.9 EQ347L

C	Si	Mn	Cr	Ni	Mo	N	Nb
0.03	0.65	1.0-2.5	19.0-21.0	9.0-11.0	0.75	-	0.50-0.80

Strip

Stainless Steel



WS-22 12 LNb

Classification: ISO 14343-A B 22 12 LNb
SFA/AWS A 5.9 EQ309LNb

C	Si	Mn	Cr	Ni	Mo	N	Nb
0.03	0.50	1.0-2.5	20.0-23.0	11.0-13.0	0.75	-	0.50-0.80

WS-2209

Classification: ISO 14343-A B 22 9 3 NL
SFA/AWS A 5.9 EQ 2209

C	Si	Mn	Cr	Ni	Mo	N	Nb
0.03	1.0	2.5	21.0-24.0	7.0-10.0	2.5-4.0	0.1-0.2	-

WS-410

Classification: ISO 14343 B 13
SFA/AWS A 5.9 EQ 410

C	Si	Mn	Cr	Ni	Mo	N	Nb
0.15	0.90	1.0	12.0-15.0	-	-	-	-

WS-420

Classification: ISO 14343-B BS 420
SFA/AWS A 5.9 EQ 420

C	Si	Mn	Cr	Ni	Mo	N	Nb
0.25-0.40	0.50	0.60	12.0-14.0	-	-	-	-

WS-430

Classification: ISO 14343-A B 17
SFA/AWS A 5.9 EQ 430

C	Si	Mn	Cr	Ni	Mo	N	Nb
0.10	0.90	1.0	15.5-17.0	-	-	-	-

Strip

Nickel-based Alloy



WS-NICKEL-6625

Classification: ISO 18274 B Ni 6625
SFA/AWS A 5.14 ER NiCrMo-3

C	Si	Mn	Cr	Ni	Mo	Fe	Nb+Ta
0.10	0.50	0.50	20.0-23.0	≥58	8.0-10.0	≤5.0	3.0-4.2

WS-NICKEL-6082

Classification: ISO 18274 B Ni 6082
SFA/AWS A 5.14 ER NiCr-3

C	Si	Mn	Cr	Ni	Mo	Fe	Nb+Ta
0.03	0.50	2.5-3.5	18.0-22.0	≥67	-	≤3.0	2.0-3.0